

این محصول یک مقوای دو تا چهار لایه از کاغذهای بازیافتی می‌باشد. وایت تاپ لاینر محصولی است که تماماً از خمیر بازیافتی قهوه‌ای در دو، سه یا چهار لایه ساخته می‌شود. در برابر کشیدگی و ترکیدگی مقاومت نسبتاً بالایی دارد. میزان جذب آب آن نیز طبق سفارش مشتری قابل تنظیم است و برای مصارف سردخانه‌ای مقاومت آن در برابر رطوبت بیشتر می‌باشد.



مشخصات نزدیک به محصول شبه کرافت لاینر با صرفه اقتصادی، دارای مقاومت نسبتاً خوب در مقابل جذب آب، کیفیت سطحی مناسب جهت استفاده در لایه بیرونی یا داخلی کارتن

استفاده در لایه داخلی یا بیرونی کارتن

White Top Liner

- **Product Name**
وایت تاپ لاینر
- **Brand Name**
KAVIR WTL
- **Type**
White Top Liner
- **Grammages**
۱۲۵-۳۵۰
- **Color**
White



White Top Liner

Physical Properties	Unit Grade	Rate	KAVIR WTL								
Grammage	g/m ²	Ave	125±4%	140±4%	160±4%	180±4%	200±4%	220±4%	250±4%	300±4%	350±4%
Moisture	%	Ave	8±1	8±1	8±1	8±1	8±1	8±1	8±1	8±1	8±1
Burst Index	kpa.m ² /g	min	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Cobb(60s)	g/m ²	Ave	20-50	20-50	20-50	20-50	20-50	20-50	20-50	20-50	20-50
RCT(GM)	KN/m	min	>1.1	>1.3	>1.5	>1.6	>2	>2.2	>2.4	>2.8	>3
Smoothness	s	Ave	11	12	12	12	15	17	19	21	25

WHITE TOP LINER

White Top Liner

● Brand Name

KAVIR WTL

● Product Name

White Top Liner

● Grammages

125 - 350

● Type

White Top Liner

● Color

White

An economic product close to semi-Kraft Liner in specifications, high water resistance, suitable quality to use as the outer or liner layer of carton.

Top Surface



Bottom surface



Inner or outer layer of the carton.



This product is a two and/or four-layer paperboard made of recycled paper. The product is entirely made of recycled brown pulp in two, three or four layers with a relatively high physical properties to tensile and bursting. Water resistance can be customized, possible to increase the water resistance for cold storage purposes.

White Top Liner

Physical Properties	Unit Grade	Rate	KAVIR WTL								
Grammage	g/m ²	Ave	125±4%	140±4%	160±4%	180±4%	200±4%	220±4%	250±4%	300±4%	350±4%
Moisture	%	Ave	8±1	8±1	8±1	8±1	8±1	8±1	8±1	8±1	8±1
Burst Index	kpa.m ² /g	min	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Cobb(60s)	g/m ²	Ave	20-50	20-50	20-50	20-50	20-50	20-50	20-50	20-50	20-50
RCT(GM)	KN/m	min	>1.1	>1.3	>1.5	>1.6	>2	>2.2	>2.4	>2.8	>3
Smoothness	s	Ave	11	12	12	12	15	17	19	21	25